

#### **TECHNICAL DATA SHEET FOR**

# SOLAREFLECT

DESCRIPTION	:	SolaReflect is a 100% acrylic elastomeric cool coating. It satisfies SS500:2015 specification for the elastomeric coating that helps to prevent or cover hair line cracks Additionally, SolaReflect reflects a large amount of solar radiation from the sun, reducing heat build-up with COOL-TEC technology.
ТҮРЕ	:	100% acrylic elastomeric polymer
COLOUR	:	As per colour card
FINISH	:	Low Sheen
USES	:	<ul> <li>High performance coating system for use on external masonry wall surfaces such as concrete, cement plastered wall and brickwork.</li> <li>Warehouse, factory and cold storage room.</li> </ul>
FEATURES	:	<ul> <li>Excellent weather resistance</li> <li>Long lasting colours</li> <li>Excellent dirt pick-up resistance</li> <li>Elastic and flexible with good performance in tensile strength that are able to cover existing and potential hairline cracks</li> <li>Excellent resistance to alkali and efflorescence</li> <li>Water repellent</li> <li>Water vapour permeable</li> <li>Anti-carbonation property</li> <li>Excellent resistance to fungal and algal growth</li> <li>Non-toxic, does not contain lead, mercury and heavy metals</li> <li>Environmentally friendly paint certified under the Singapore Green Building Product Certification Scheme, Solar reflective paint category</li> </ul>
APPLICATION DATA		
METHOD	:	Brush, roller, airless spray or air spray
RECOMMENDED APPLICATION THICKNESS	:	40 – 50 microns DFT
THEORETICAL COVERAGE	:	10–12 m <sup>2</sup> /litre (based on 40 microns DFT)
DILUTION	:	No dilution is necessary for best performance

### TECHNICAL DATA SHEET FOR

## SOLAREFLECT

SPRAY APPLICATION	:	Delivery Pressure Tip Size Spray Angle Dilution with water	<u>Air</u> 3 ~ 4 Kg/cm <sup>2</sup> 1.3mm 50 - 70° 10 ~ 20%	<u>Airless</u> 140 – 200 kg/cm <sup>2</sup> 0.017" – 0.023" 50 - 70° 10% max
SURFACE PREPARATION	:	Ensure surface is clean surface treatments:	, dry and stable using th	ne following suggested
			ust not be any water res ure must be <4% (Sove	
		etc by high-pressure	emove loose bonding fi water jet wash or mec per, whichever is suitab	hanical means such as
			move dust and foreign r e oil or grease using sol	
			: Wash the affected are organisms. Apply Anti-Fi 2 hours	
		Hairline cracks :Fill resistant putty or fill	I cracks with suitable ex er	terior grade water-
DRYING TIME	:	Surface Dry - 30 minut Hard Dry - 2 Hours at 3		
OVERCOATING TIME	:	2 hours based on norm	nal conditions	
RECOMMENDED PAINTING SYSTEM	:		ct Sealer-Primer White ( ect (40-50 microns DFT	
		Powdery substrate is recommer painting system	ided to apply Vinilex 5170 oil-bas	sed sealer follow by the above
CLEANING	:	All equipment should b	e cleaned with water im	mediately after use.
GENERAL INFORMATION				
SOLID CONTENT	:	$61 \pm 2\%$ by weight (ba	sed on white colour)	
SPECIFIC GRAVITY	:	$1.38 \pm 2\%$ kg/litre (bas	ed on white colour)	
PACKING	:	20 litres		

#### **TECHNICAL DATA SHEET FOR**

### SOLAREFLECT

STORAGE	:	Store in a tightly sealed container below 30°C.
SHELF LIFE	:	Up to 24 months in a tightly sealed container.
PRECAUTION	:	Avoid painting when the temperature is below 10°C or when the humidity is over 85%. Ensure adequate protection and avoid direct contact on sensitive skin, eye, etc. Refer to the product Safety Data Sheet for more information.

The information given is intended to give a description of the product performance under specific test conditions. Nevertheless, we cannot assume any responsibility for the use of it since circumstances under which the products are applied in practice are subjected to many variations. We reserve the right to alter the given data without notice.

:

Enquiries / Contact Details

Customer Service 6265 5355 (Main Line) 6264 1603 (Fax) www.nipponpaint.com.sg