

## TECHNICAL DATA SHEET FOR

## FLOOR-PRO 328 SF DECORATIVE EPOXY FINISH

**FLOOR-PRO 328 SF DECORATIVE EPOXY FINISH** is a two-component, solvent-free multi-coloured epoxy topcoat formulated with premium special grade epoxy binder.

### FEATURES

- Solvent-free, low odour
- 100% solid pure resin gives higher crosslinking for improved mechanical and chemical resistance
- Seamless

### APPLICATION AREAS

- Used as a decorative durable top coat for industrial, commercial & institutional usages
- Specifically designed as multi-coloured epoxy to simulate natural granites, and other urban expressions and designs

### PHYSICAL PROPERTIES

<b>Chemical Composition</b>	Solvent-free epoxy
<b>Colour</b>	As per standard colours
<b>Finish</b>	Gloss
<b>Density, mixed</b>	1.15 g/cm <sup>3</sup> @ 30°C
<b>Viscosity, mixed</b>	2000 - 3000 cps @ 30°C
<b>Solid Content, mixed</b>	100 % (By weight)

### PERFORMANCE DATA

<b>Adhesive strength</b>	>1.5 N/mm <sup>2</sup> (Concrete failure)
<b>Compressive strength</b>	> 80.0 N/mm <sup>2</sup> (ASTM C579)
<b>Taber Abraser Wear Index</b>	50 mg / 1000 revolutions (ASTM D 4060)
<b>Shore D hardness</b>	> 80 (ASTM D2240)
<b>Light fastness (Scale 1-8, 8=best)</b>	6 (DIN EN ISO 105-B02)

\*Conditions such as installation process, inappropriate maintenance, short and long-term wear and use as well as surface contaminants (wet or dry) affects the slipperiness of flooring materials. To meet slip resistance requirement for wet conditions and/or surface contaminants (wet or dry), appropriate textured or anti-slip floor systems are recommended. Please contact Nippon Paint for further details and specifications.

\*\*The final floor finish shall follow the profile of the concrete, therefore appropriate levelling compound is recommended to treat the undulating surface.

### APPLICATION GUIDE

<b>Mixing Ratio (by weight)</b>	Part A : Part B 3.44 : 1.56
<b>Number of coats</b>	1 - 2 coats
<b>Recommended Thickness</b>	170 – 850 mm DFT per coat
<b>Theoretical Coverage</b>	0.2 – 1.0 Kg/m <sup>2</sup> /coat
<b>Recoating time</b>	Within 24 - 72 hrs @ 28°C
<b>Pot Life (Working time)</b>	20 mins @ 28°C
<b>Curing time</b>	30°C Foot traffic (hrs) 18

	Light traffic (days)	3
	Exposure to chemicals (days)	7
<b>Substrate Temperature relative to dew point</b>	$\geq 3^{\circ}\text{C}$	
<b>Recommended application temperature range</b>	Minimum $15^{\circ}\text{C}$ Maximum $35^{\circ}\text{C}$	
<b>Relative Humidity</b>	$< 85\%$	

### SUBSTRATE REQUIREMENTS

- Concrete or screed substrate compressive strength should be of minimum  $25 \text{ N/mm}^2$  and adhesive pull off strength of  $1.5 \text{ N/mm}^2$ .
- The moisture content of concrete shall be  $< 4\%$  or dried up to  $85\% \text{ RH}$  as per BS8204. It shall be free from rising damp and must be waterproofed against negative ground water pressure.

### SURFACE PREPARATION

- Concrete substrate must be clean, free of laitance and contaminants.
- In the event the moisture content is  $> 4\%$ , FLOOR-PRO 203 SL EPOXY MOISTURE BARRIER may be applied as temporary moisture barrier system.
- Allow to cure over-night before the application of subsequent coating system. Prepare the concrete substrate surface by captive shot blasting, scarifying or mechanical grinding. Repair damaged area and patch up cracks and holes using a suitable repair material compatible with the coating system.

### APPLICATION METHOD

- The products in the system are multi-components and pre-packed in sets. Each set requires effective and homogenous mixing using drill and helical spinner with the least inclusion of air in a clean mixing barrel prior to applying.
- FLOOR-PRO 328 SF DECORATIVE EPOXY FINISH is proportioned 2-component products which are spread on the floor by squeegee and finished with roller
- If reworking within 48 hours after application the coating need not be sanded. Reworking later than that is only possible after sanding it carefully.

### PACKAGING

Components	PART A (BASE)	PART B (HARDENER)
<b>TOTAL 5 Kg</b>	3.44	1.56

### STORAGE AND SHELF LIFE

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care. (Unopened and in good condition temperature  $15^{\circ}\text{C}$  to  $35^{\circ}\text{C}$ )

Components	PART A (BASE)	PART B (HARDENER)
<b>Months</b>	12	12

**SAFETY PRECAUTION**

- This product is intended for use by professional applicators. Refer to the safety information display on the container and in the safety data sheet (SDS) before using the product.
- Use this product in well-ventilated area, avoid skin contact, spillage on the skin should immediately be removed with suitable cleanser, soap and water.
- Eye should be well flushed with water and seek for medical attention immediately upon contact with this product.
- During the application, naked flame, welding operation and smoking is not allowed. Adequate ventilation should be provided.
- If you have any doubt regarding the suitability of use, refer to Nippon Paint for further advice.

**DISCLAIMER**

**The information in this data sheet is given to the best of Nippon Paint's knowledge and practical experience. Users may consult with Nippon Paint on the general suitability of the product for their needs and specific application practices though it remains each user's responsibility to determine the suitability of the product for the user's particular use. The condition of the substrate and application are not within Nippon Paint's control. Therefore, no implied conditions, warranties or other terms will apply to the Product. Nippon Paint does not and cannot warrant the results which the user may obtain by using the product. In no event will Nippon Paint be liable to the user for any kind of loss (whether direct or indirect) even if Nippon Paint was previously advised of it. In line with Nippon Paint's policy for continuous development, Nippon Paint reserves the right to modify the product and the information in this data sheet without prior notice. It is the user's responsibility to check with Nippon Paint for the latest version of this data sheet. This data sheet has been translated into various languages. In the event of any inconsistency, the English version shall prevail.**