

TECHNICAL DATA SHEET FOR

FLOOR-PRO 904 SF SCRATCH COAT

FLOOR-PRO 904 SF SCRATCH COAT is a two-component solvent-free epoxy resin filled resurfacing scratch coat

FEATURES

- Solvent-free, low odour
- Seamless & hygienic finish when sealed
- Low maintenance
- High impact resistance
- Heavy duty for traffic
- Excellent chemical resistance

APPLICATION AREAS

- Areas for use in industrial floor, warehouse, chemical plants, manufacturing areas and car parks. To provide protection for area subjected to heavy traffic, impact and chemical areas.

Note: Product is not colour stable if exposed to UV light, hence it is recommended to finish with UV resistant topcoat to enhance the durability.

PHYSICAL PROPERTIES

Chemical Composition	Solvent-free epoxy seal coat
Colour	Natural
Density, mixed	2.20 ± 0.1 g/cm ³ @ 28°C
Solid Content, mixed	100 % by weight

PERFORMANCE DATA

Adhesive strength	>2.0 N/mm ² (Concrete failure)
Compressive Strength	70 N/mm ² @ 28 days
Flexural Strength	30 N/mm ²
Tensile strength	22 N/mm ²
Impact Resistance	0.30 mm (BRE Screed Tester)

*Conditions such as installation process, inappropriate maintenance, short and long-term wear and use as well as surface contaminants (wet or dry) affects the slipperiness of flooring materials. To meet slip resistance requirement for wet conditions and/or surface contaminants (wet or dry), appropriate textured or anti-slip floor systems are recommended. Please contact Nippon Paint for further details and specifications.

**The final floor finish shall follow the profile of the concrete, therefore appropriate levelling compound is recommended to treat the undulating surface.

APPLICATION GUIDE

Mixing Ratio (by weight)	Part A : Part B 8 : 2
Number of coats	1-2 coats
Theoretical Coverage	0.3 – 0.5 Kg/m ² /coat
Pot Life (Working time)	45 mins @ 28°C
Recoating time	12 hrs

Curing time		20°C	30°C
	Foot traffic (hrs)	24	16
	Light traffic (hrs)	72	48
	Exposure to chemicals (days)	10	7
Substrate Temperature relative to dew point	≥ 3°C		
Recommended application temperature range	Minimum 5°C Maximum 40°C		
Relative Humidity	< 85%		

SUBSTRATE REQUIREMENTS

- Concrete or screed substrate compressive strength should be a minimum of 25 N/mm² and adhesive pull off strength of 1.5 N/mm².
- The moisture content of concrete shall be < 4% or dried up to 85% RH as per BS8204. It shall be free from rising damp and must be waterproofed against negative ground water pressure.

SURFACE PREPARATION

- Concrete substrate must be clean, free of laitance and contaminants.
- Allow to cure over-night before the application of subsequent painting system. Prepare the concrete substrate surface by captive shot blasting, scarifying or mechanical grinding. Repair damaged area and patch up cracks and holes using a suitable repair material compatible with the coating system.

APPLICATION METHOD

- Pour total Part B into the Part A container and mix both liquids thoroughly for one minute by using a suitable electrical stirrer (with 750 watt high power mixer) until a fully homogenous mix has been achieved. Transfer the mixed material to a clean container and mix for another minute.
- FLOOR-PRO 904 SF SCRATCH COAT can be applied by suitable roller as a primer for sealing well the substrate porosity
- Apply the mixed FLOOR-PRO 904 SF SCRATCH COAT with roller as seal coat to seal porosity of FLOOR-PRO 202 SF EPOXY MORTAR

PACKAGING

Components	PART A (BASE)	PART B (HARDENER)
TOTAL 10 Kg	8	2

STORAGE AND SHELF LIFE

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care. (Unopened and in good condition temperature 10°C to 30°C)

Components	PART A (BASE)	PART B (HARDENER)
Months	12	12

SAFETY PRECAUTION

- This product is intended for use by professional applicators. Refer to the safety information display on the container and in the safety data sheet (SDS) before using the product.
- Use this product in well-ventilated area, avoid skin contact, spillage on the skin should immediately be removed with suitable cleanser, soap and water.
- Eye should be well flushed with water and seek for medical attention immediately upon contact with this product.
- During the application, naked flame, welding operation and smoking is not allowed. Adequate ventilation should be provided.
- If you have any doubt regarding the suitability of use, refer to Nippon Paint for further advice.

DISCLAIMER

The information in this data sheet is given to the best of Nippon Paint's knowledge and practical experience. Users may consult with Nippon Paint on the general suitability of the product for their needs and specific application practices though it remains each user's responsibility to determine the suitability of the product for the user's particular use. The condition of the substrate and application are not within Nippon Paint's control. Therefore, no implied conditions, warranties or other terms will apply to the Product. Nippon Paint does not and cannot warrant the results which the user may obtain by using the product. In no event will Nippon Paint be liable to the user for any kind of loss (whether direct or indirect) even if Nippon Paint was previously advised of it. In line with Nippon Paint's policy for continuous development, Nippon Paint reserves the right to modify the product and the information in this data sheet without prior notice. It is the user's responsibility to check with Nippon Paint for the latest version of this data sheet. This data sheet has been translated into various languages. In the event of any inconsistency, the English version shall prevail.