

**PRODUCT DESCRIPTION**

**Hi-Floro 6738 Fluorocarbon Top Coat** is a two-pack, fast dry fluorocarbon finish coat. It provides excellent film stability, good resistance of contamination, weathering and chemicals.

**INTENDED USE**

It is designed for use as a long-term protection of high-performance finish especially for structures with higher requirements of contamination resistance and weathering resistance, such as bridges, petrochemicals, power generations, steel structures and other steel works.

**GENERAL PROPERTIES**

<b>Colour</b>	: Colour range based on assortment list
<b>Gloss Level</b>	: Gloss
<b>Volume Solid</b>	: 46 ± 2 %
<b>Specific Gravity</b>	: 1.20 ± 0.15 kg/l (Mixed) – depending on colours
<b>Flash Point</b>	: Base: 13.3 °C Hardener: 24 °C Mix: 13.3 °C
<b>VOC</b>	: 480 g/L (EPA Method 24)
<b>Typical Thickness</b>	: 25 – 60 µm dry film 54 – 130 µm wet film

**SURFACE PREPARATION**

All surfaces should be clean dry, and free from contamination. The surface should be assessed and treated in accordance with ISO 8504. Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Damaged Area

Damage area should be prepared with abrasive blast cleaning to Sa 2½ (ISO 8501-1) or SSPC-SP10. When abrasive blasting is not possible, mechanical cleaning to St3 (ISO 8501-1) or SSPC-SP3 is acceptable. After the surface preparation, patch suitable primer prior to the application of Hi-Floro 6738.

Other Surfaces

The coating may be used on other substrates. Please contact your local Nippon Paint office for more information.

**CONDITION DURING  
APPLICATION**

Avoid paint application when the temperature is below 10 °C and relative humidity is above 85 %. The temperature of steel surface must be minimum 3 °C above dew point of surrounding air.

**APPLICATION GUIDE**

<b>Mixing Ratio</b>	:	<b>BASE</b>	:	<b>HARDENER</b>	
		14	:	1	(by volume)
		Base and hardener should be mixed			

thoroughly before use with a mechanical agitator

<b>Pot Life</b>	: <u>25 °C</u> 6 hours
<b>Theoretical Coverage</b>	: 18.4 m <sup>2</sup> /litre at 25 µm DFT 7.7 m <sup>2</sup> /litre at 60 µm DFT
<b>Thinner</b>	: Hi-Floro 6738 Thinner
<b>Cleaner</b>	: Hi-Floro 6738 Thinner

### APPLICATION METHOD

Conventional air and airless spray are recommended for application. Brush and roller are recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.

### APPLICATION DETAILS

<b>Airless Spray</b>	: Tip Size	: 0.011" – 0.018"
	: Pressure at nozzle	: 100 – 150 bar
<b>Drying Time</b>	: Substrate Temperature	<u>25 °C</u> <u>40 °C</u>
	Surface Dry	30 mins    20 mins
	Through Dry	4 hrs    2 hrs
	Cured	7 days    3 days
	Dry to Overcoat (min)	4 hrs    2 hrs
	Dry to Overcoat (max)*	14 days    14 days

\*Can be extended

**Remarks:** Where an "extended" overcoating time is stated, consult Nippon Paint Protective Coatings for recommended surface preparation to achieve optimal intercoat adhesion.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

### HEAT RESISTANCE

#### Dry, Atmospheric

- Continuous : 100 °C
- Minimum : - 40 °C
- Intermittent : 150 °C

Intermittent temperature duration – 1 hour maximum

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures. Heat resistance is influenced by the total coating system. If used as part of a system, ensure all coatings in the system have similar heat resistance.

**RECOMMENDED  
COATING SYSTEM**

The following coating systems are recommended for Hi-Floro 6738 Fluorocarbon Top Coat:

**Primer:**

- Zinky-12 Inorganic Zinc Rich Primer 77
- Zinky-13 Inorganic Zinc Rich Primer 85
- Zinky-22 Epoxy Zinc Rich Primer 80
- Zinky-23 Epoxy Zinc Rich Primer 85
- Hi-Pon 20-03 Epoxy Red Oxide Primer
- Hi-Pon 20-04 STE 80
- Hi-Pon 20-04 STE IM 80
- Hi-Pon 20-07 Epoxy Zinc Phosphate 70
- Hi-Pon 20-10 Epoxy Zinc Phosphate 63

**Intermediate:**

- Hi-Pon 20-04 STE 80
- Hi-Pon 20-04 STE IM 80
- Hi-Pon 30-02 Epoxy MIO 80
- Hi-Pon 30-03 Epoxy Midcoat 80
- Hi-Floro 6738 Undercoat EP
- Hi-Floro 6738 Fluorocarbon Undercoat

For the choice of coating system for different application, refer to the product brochure or contact Nippon Paint for professional recommendation.

**PACKAGING**

<u>Unit</u>	<u>Base</u>		<u>Hardener</u>	
	<b>Volume</b>	<b>Container Size</b>	<b>Volume</b>	<b>Container Size</b>
<b>15 L</b>	14 L	20 L	1 L	1 L

**STORAGE**

**Shelf Life**      Base : 12 months (25 °C) minimum  
                           Hardener : 12 months (25 °C) minimum

Subject to re-inspection thereafter. Higher temperature during storage may reduce the shelf life and may lead to gelling in the tin. Frequent temperature cycles may also shorten the shelf life.

Store in tightly closed container in a dry, cool and well-ventilated space, keep away from sources of heat and ignition.

**SAFETY PRECAUTION**

- This product is intended for use of professional applicators. Refer to the safety information display on the container and in the safety data sheet (SDS) before using the product.
- Use this product in well-ventilated area, avoid skin contact, spillage on the skin should immediately be removed with suitable cleanser, soap and water.
- Eye should be well flush with water and seek for medical attention immediately upon contact with this product.
- During the application, naked flame, welding operation and smoking is not allowed. Adequate ventilation should be provided.
- If you have any doubt regarding the suitability of use, refer to Nippon Paint for further advice.

**DISCLAIMER**

The information in this data sheet is given to the best of Nippon Paint's knowledge and practical experience. Users may consult with Nippon Paint on the general suitability of the product for their needs and specific application practices though it remains each user's responsibility to determine the suitability of the product for the user's particular use. The condition of the substrate and application are not within Nippon Paint's control. Therefore, no implied conditions, warranties or other terms will apply to the Product. Nippon Paint does not and cannot warrant the results which the user may obtain by using the product. In no event will Nippon Paint be liable to the user for any kind of loss (whether direct or indirect) even if Nippon Paint was previously advised of it. In line with Nippon Paint's policy for continuous development, Nippon Paint reserves the right to modify the product and the information in this data sheet without prior notice. It is the user's responsibility to check with Nippon Paint for the latest version of this data sheet. This data sheet has been translated into various languages. In the event of any inconsistency, the English version shall prevail.