

Marine Paint Manual

Reference No. : 14 - 13

Issue Date: March 2014 (ES)

NOA PC

A two-pack pure epoxy designed for petroleum and chemical product tanks. It offers superior resistance to petroleum products, solvents, water and chemical attack.

1st Buff colour is characterized by Self Indicating (SI) technology, which enables a painter to visually judge if the correct film thickness (wet / dry) has been achieved during the application process and after the completion of painting. Two coat system with SI paint (1st coat) plus non-SI paint (2nd coat) is recommended.

Suitable Use	Product Carriers, Tanks for petroleum products			
Type	Pure epoxy (High build / Two-pack)			
Colour	1st coat : Buff 2nd coat : Gray (Non-SI)			
Gloss	Semi-gloss			
Volume Solids	65 ± 2% (ISO3233:1998)			
Dry Film Thickness	125 ~ 300 µm			
Approx. Wet Film Thickness	192 ~ 462 µm			
Theoretical Coverage	5.20 m ² / L (125 µm)			
Drying Time	Surface Dry	3½ hours (5°C)	1½ hours (20°C)	40 minutes (30°C)
	Dry Hard	36 hours (5°C)	16 hours (20°C)	10 hours (30°C)
Interval before Overcoating (by self)	Min.	36 hours (5°C)	16 hours (20°C)	10 hours (30°C)
	Max.	10 days (5°C)	7 days (20°C)	5 days (30°C)
Thinner	NIPPON MARINE THINNER 600 (0 ~ 5%, by weight)			
Application Method	Airless Spray	Tip range	0.48 ~ 0.53 mm	
		Fan range	45 ~ 60°	
		(T/U)	30°	
		Output pressure	150 ~ 200 kg / cm ²	
	Brush	For touching up small areas only		
Mixing Ratio by Volume	BASE 3.57 / HARDENER 1			
Pot Life after Mixing	5 hours (5°C)	3 hours (20°C)	2½ hours (30°C)	
Typical Package	16L (BASE 12.2L / HARDENER 3.5L)			
	Package may vary from country to country.			
Japan Local Brand	NIPPE EPOXY PC NOA			
Flash Point	BASE 14° C	HARDENER 6° C		
Surface Preparation	Blast cleaned to ISO-Sa 2.5 is recommended			
Safety	Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.)			
	Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapour concentrations within safe limits.			
	Prior to use, obtain, consult and follow the MSDS for this product concerning health and safety information.			

Marine Paint Manual

NOA PC

Issue Date: April 2010 (ES)

< Note >

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Apply this paint immediately after sandblasting. Before painting, the areas where corroded, welded and burnt should be carefully treated with sandblasting, shotblasting, or a disc sander or a power brush.
- 3) If half-dried painted surface is subjected to rain or dew, blooming or sweating may occur, with the surface turned to white. Rub the area lightly with a wire brush before painting.
- 4) For the applications, refer to our "Suitability Table of Cargoes for Loading" and "Application Manual of NOA PC System".
- 5) Store the paints in paint store.