

## TECHNICAL DATA SHEET FOR

**SOLAREFLECT COOLFLOOR MIDCOAT**

<b>DESCRIPTION</b>	:	SolaReflect CoolFloor Midcoat is a 2-component water-based Acrylic Epoxy Hybrid (AEH) cool coating. It uses COOL-TEC technology to enhance SolaReflect CoolFloor Topcoat's solar reflective properties. Moreover, it is used to create films build that can accept aggregates for superior slip and skid resistance. The product is suitable for asphalt, pavement, and concrete floors.
<b>TYPE</b>	:	2 component water-based Acrylic Epoxy Hybrid (AEH) midcoat
<b>COLOUR</b>	:	White
<b>FINISH</b>	:	Semi-gloss
<b>USES</b>	:	For pavement, asphalt, and concrete surfaces to enhance solar reflective properties and as a body coat to accept anti-skid aggregates
<b>FEATURES</b>	:	<ul style="list-style-type: none"><li>• High solar radiation reflection, less heat build-up results in improved thermal comfort</li><li>• Good Resistance to aggressive and severe weather conditions</li><li>• Durable, high hardness and good abrasion resistance</li><li>• Low water absorption and water vapour permeable</li><li>• Chemical and corrosion resistance properties</li><li>• Long pot life with excellent application workability</li><li>• Water- based formulation that is safe, easy to apply and fast drying</li><li>• Non-toxic, does not contain lead, mercury and heavy metals</li><li>• Environmentally friendly paint certified under the Singapore Green Building Product Certification Scheme</li></ul>

**APPLICATION DATA**

<b>METHOD</b>	:	Squeegee, roller and brush Pour the mixed material onto the primed substrate in portion, and spread with a squeegee and back roll with a roller
<b>THEORETICAL COVERAGE</b>	:	On concrete: 0.2 ~ 0.4 Kg / m <sup>2</sup> at dry film thickness of 50 µm per coat On asphalt & pavement: 0.3 ~ 0.5 Kg / m <sup>2</sup> at dry film thickness of 50 µm per coat
<b>THEORETICAL COVERAGE OF NON-SKID AGGREGATE</b>	:	Full broadcast on SolaReflect CoolFloor Midcoat: 1.0 – 1.5 Kg / m <sup>2</sup>
<b>DILUTION</b>	:	No dilution is necessary for best performance
<b>MIXING RATIO</b>	:	Part A : Part B = 1:1 (by weight)

**SOLAREFLECT COOLFLOOR MIDCOAT**

- POT LIFE** : 4 Hrs at 25 °C  
Important note: Do not use mixed materials beyond the recommended pot-life of 4 hours. As Part B is sensitive to the weather, only open the Hardener (Part B) portion when required for mixing and close tightly after use
- SURFACE PREPARATION** : Ensure surface is clean, dry and stable. Concrete substrate must be primed with SolaReflect CoolFloor Primer after using the following suggested surface treatments:
- **Moisture:** There must not be any water residue on the surface of the substrate. Moisture must be <4% (Tramex CME4 moisture master) before application
  - **Unstable matter:** Remove loose bonding film, dirt, peeling paint, etc by high-pressure water jet wash or mechanical means such as grinding, sanding, scarifying, power brush or scraper, whichever is suitable
  - **Contaminants:** Remove dust and foreign matter by cleaning with damp cloth. Remove oil or grease using alkaline degreaser, detergent or solvent. Allow surface to dry
  - **Fungus and Algae:** Wash the affected area to remove unstable matters and micro-organisms. Apply Anti-Fungus Solution and leave on for at least 2 hours
  - **Undulated Substrate:** Levelling with FLOOR-PRO 202 SF EPOXY MORTAR or FLOOR-PRO 501 RE-SURFACING SCREED or any compatible levelling compound to achieve the desired flatness
- DIRECTION OF USE** : **Mixing**  
Stir each component separately using an electric drill fitted with a paint mixer or a wing type mixing paddle. Pour the entire contents of Part B into Part A while stirring and mix evenly for approximately 5 minutes until a homogenous tone is achieved.
- Important note: Do not attempt to mix the both component manually, mechanical stirrer must be used to assure the effective mixing**
- DRYING TIME** : Touch Dry – 30 mins at 30 °C  
Hard Dry – 2 hours at 30 °C
- OVERCOATING TIME** : 2 hours minimum at 30 °C

**SOLAREFLECT COOLFLOOR MIDCOAT**

- RECOMMENDED PAINTING SYSTEM** :
- Primer: 1 coat of SolaReflect CoolFloor Primer
  - Midcoat: 1 coat of SolaReflect CoolFloor Midcoat
  - Non-skid aggregate
  - Topcoat: 2 coats SolaReflect CoolFloor Topcoat
- CLEANING** : All equipments should be cleaned with water immediately after use

**GENERAL INFORMATION**

**SOLID CONTENT** : 60.0 ± 2.0 % by weight (mixture, based on white colour)

**SPECIFIC GRAVITY** : 1.17 – 1.37 kg / litre (mixture, based on white colour)

**PACKING** :

Unit	Part A		Part B	
	Weight	Container Size	Weight	Container Size
20 KG	10 KG	20 L	10 KG	20 L

**STORAGE** : Store in a tightly sealed container in a cool, dry place

**SHELF LIFE** :

Part A	Part B
6 Months	12 Months

**PRECAUTION** : Ensure good ventilation during application and drying of paint. Avoid direct contact with sensitive skin. Use appropriate personal protective equipment

Refer to the product Safety Data Sheet for more information

The information given is intended to give a description of the product performance under specific test conditions. Nevertheless, we cannot assume any responsibility for the use of it since circumstances under which the products are applied in practice are subject to many variations. We reserve the right to alter the given data without notice.

**Enquiries / Contact Details** :

**Customer Service**  
 6265 5355 (Main Line)  
 6264 1603 (Fax)  
[www.nipponpaint.com.sg](http://www.nipponpaint.com.sg)